

- aqueous pigment preparations
- for gravimetric and volumetric dosage
- VOC-free
- according to RAL-UZ 102
- free of binders and solvents
- homogeneous
- highly concentrated
- optimal particle size
- the majority are resistant to drying out and freezing
- good compatibility with wide variety of aqueous binders
- wide variety of application forms
- wide selection of organic and inorganic preparations
- the preparations are available with a range of fastness properties (weather/temperature) depending on the application required

Preferred applications:

Paints and varnishes industry: wood print inks, stains, dispersion paints and varnishes, industrial varnishes, paints, varnishes, fillers, full-tone pigments for dispersion colours, wood varnishes, interior and exterior wood coatings, artist's paints (acrylic), hobby paints, full-tone paints., road marking paints, finger paint, special paints for mouth painting, tinting systems, glass varnish

Printing inks industry: Flexographic printing inks, printing inks, printing inks for cardboard articles and paper, printing inks for tissue, printing inks for packaging, wallpaper printing inks, flooring printing inks (e.g. for linoleum)

Building industry: acrylic and silicate plaster, silicone plaster and paints, buildings, building protection, wood protectant, polyvinyl acetate and acrylic based dispersions paints, various adhesives and flooring compounds

Leather industry: leather colours

Paper and paints: decorating paints, paper, tissue

Industry: plastic casings (phono, mobile telephones), glues

Food and textile industry: textile dyes, viscose, textile auxiliaries (finishing agents, additives)

Office supplies industry: writing inks

| Colour Index | Product name | Pigment content |
|---------------------|---|------------------------|
| Mixture | Vocaflex-LF Umbra | 67 % |
| PB 15 | Vocaflex-LF Blue 15 | 45 % |
| PB 15:1 | Vocaflex-LF Blue 15:1 | 49 % |
| PB 15:3 | Vocaflex-LF Blue | 50 % |
| PB 15:6 | Vocaflex-LF Blue 15:6 | 27 % |
| PB 28 | Vocaflex-LF Cobalt Blue 28 | 65 % |
| PB 29 | Vocaflex-LF Ultramarine Blue | 60 % |
| PB 36 | Vocaflex-LF Cobalt Blue 36 | 62 % |
| PBr 24 | Vocaflex-LF Chrome Titanium Yellow (CrTi) | 67 % |
| Mixture | Vocaflex-LF Brown | 58 % |
| PG 17 | Vocaflex-LF Chromoxide Green 17 | 71 % |
| PG 50 | Vocaflex-LF Cobalt Green | 70 % |
| PG 7 | Vocaflex-LF Green | 42 % |
| PG 7 | Vocaflex-LF Green 7 | 53 % |
| PG 36 | Vocaflex-LF Green 36 | 50 % |
| PO 5 | Vocaflex-LF Orange 5 | 47 % |
| PO 34 | Vocaflex-LF Orange 34 | 43 % |
| PO 73 | Vocaflex-LF Orange 73 | 41 % |
| PR 3 | Vocaflex-LF Red 3 | 43 % |
| PR 12 | Vocaflex-LF Bordeaux 12 | 39 % |
| PR 23 | Vocaflex-LF Red 23 | 42 % |
| PR 101 | Vocaflex-LF Oxide Orange 101 | 60 % |
| PR 101 | Vocaflex-LF Oxide Red 101 yellowish | 63 % |
| PR 101 | Vocaflex-LF Oxide Red 101 blueish | 62 % |
| PR 112 | Vocaflex-LF Red | 45 % |
| PR 122 | Vocaflex-LF Pink 122 | 31 % |
| PR 168 | Vocaflex-LF Scarlet Red 168 | 42 % |
| PR 184 | Vocaflex-LF Red 184 | 34 % |
| PR 210 | Vocaflex-LF Red 210 | 40 % |
| PR 254 | Vocaflex-LF Red 254 | 39 % |

| Colour Index | Product name | Pigment content |
|---------------------|--------------------------------------|------------------------|
| PV 19 | Vocaflex-LF Violet 19 | 40 % |
| PV 23 | Vocaflex-LF Violet 23 | 31 % |
| PY 1 | Vocaflex-LF Yellow 1 | 51 % |
| PY 3 | Vocaflex-LF Yellow 3 | 50 % |
| PY 138 | Vocaflex-LF Yellow 138 | 45 % |
| PY 154 | Vocaflex-LF Yellow | 35 % |
| PY 155 | Vocaflex-LF Yellow 155 | 47 % |
| PY 184 | Vocaflex-LF Bismutvanadat 184 | 64 % |
| PY 184 | Vocaflex-LF Bismutvanadat 184 | 57 % |
| PY 42 | Vocaflex-LF Oxide Yellow 42 | 60 % |
| PY 42 | Vocaflex-LF Oxide Yellow 42 reddish | 57 % |
| PY 53 | Vocaflex-LF Yellow Nickeltitan 53 | 77 % |
| PY 74 | Vocaflex-LF Yellow 74 | 50 % |
| PY 83 | Vocaflex-LF Yellow 83 | 38 % |
| PY 83 D | Vocaflex-LF Yellow 83 opaque | 45 % |
| PY 97 | Vocaflex-LF Yellow 97 | 43 % |
| PBk 11 | Vocaflex-LF Oxide Black II blueish | 58 % |
| PBk 11 | Vocaflex-LF Oxide Black II yellowish | 61 % |
| PBk 7 | Vocaflex-LF Black 7 | 44 % |
| PBk 7 | Vocaflex-LF Black 7 | 28 % |
| PW 6 | Vocaflex-LF White 6 | 63 % |